

PRE-STRETCH

KOROZO HIGH QUALITY PRE-STRETCH FILM



OUR ECONOMIC SOLUTION TO PALLET WRAP



Product Specifications

- High performance puncture and tear resistance at thinner thickness
- Better holding force because of reinforced edges
- Easy to Wrap less user energy required
- Environmental friendly and easily recyclable
- Blown Pre-stretch's dart drop is higher than cast pre-stretch film
- Blown Pre-stretch's tensile force at break is higher than cast pre-stretch film



CAST AND BLOWN MANUEL PRE-STRETCH

Available starting from 7μ to 10μ in various widths (400mm, 430mm, 450mm and Extended core).

CAST AND BLOWN MACHINE PRE-STRETCH

Available starting from 7μ to 10μ in various widths (400mm, 430mm, 450mm).

CAST PRE-STRETCH TECHNICAL SPECIFICATIONS

Properties	Values	Tolerance	Unit
Width	430	±10	mm
Thickness	7	±1	μm
Mechanical Properties	Values	Test Method	Unit
MD Tensile Strenght at Break	>100	ASTM D882	Мра
MD Tensile Force at Break	>15	ASTM D882	N
MD Tensile Elongation at Break	>90	ASTM D882	%
Dart Drop	>4	ASTM D1709	g/μm

BLOWN PRE-STRETCH TECHNICAL SPECIFICATIONS

Properties	Values	Tolerance	Unit
Width	430	±10	mm
Thickness	7	±1	μm
Mechanical Properties	Values	Test Method	Unit
MD Tensile Strenght at Break	>100	ASTM D882	Мра
MD Tensile Force at Break	>25	ASTM D882	N
MD Tensile Elongation at Break	>100	ASTM D882	%
Dart Drop	>20	ASTM D1709	g/µm

